



www.xegermany.de

SA15CHSRPS4 Technical Data

● Solar Energy Transmission	44%
● Solar Energy Reflectance.....	07%
● Solar Energy Absorption	49%
● Visible Light Transmission.....	17%
● Visible Light Reflection	05%
● Winter Median "U" Value	1.03
● Shading Coefficient.....	0.66
● Ultraviolet Rejected.....	99%
● Total Solar Energy Rejected.....	43%

Physical Properties:

● Tensile Strength Finished Film (lb/in).....	25,714
● Tensile Strength Raw Polyester (lb/in).....	32,000
● Break Strength (lb/inch).....	101
● Elongation at Break.....	100%
● Peel Strength (g/inch).....	2720
● Puncture Strength (lb).....	78