



[www.xegermany.de](http://www.xegermany.de)

## SA 35CHSRPS4 Technical Data

- Solar Energy Transmission ..... 56%
- Solar Energy Reflectance..... 07%
- Solar Energy Absorption ..... 37%
- Visible Light Transmission..... 38%
- Visible Light Reflection ..... 06%
- Winter Median "U" Value ..... 1%
- Shading Coefficient..... .76%
- Ultraviolet Rejected..... 99%
- Total Solar Energy Rejected..... 34%

## Physical Properties:

- Tensile Strength Finished Film (lb/in )..... 25.714
- Tensile Strength Raw Polyester (lb/in )..... 32.000
- Break Strength (lb/inch)..... 101
- Elongation at Break..... >100
- Peel Strength (g/inch)..... >2720
- Puncture Strength (lb)..... 78