



X^e SILVER 20 Technical Data

● Solar Energy Transmission.....	17%
● Solar Energy Reflection- Exterior.....	56%
● Solar Energy Absorption.....	27%
● Visible Light Transmission.....	22%
● Visible Light Reflection- Exterior.....	52%
● Visible Light Reflection- Interior.....	57%
● Shading Coefficient (b Value).....	0.33
● UV Transmission.....	<1%
● Emissivity.....	0.00
● U-Value (EN 673 W/m ² K)	0.0
● Glare Reduction.....	76%
● Infrared Rejection (at 1025 NW)	82%
● Total Solar Energy Rejected.....	75%

Characteristics & Benefits

- Solar control and privacy film.
- Significant improvement of working conditions due to high reduction in solar heat gain
- Reduction in air-conditioning costs and hence reduction in energy costs
- Glare reduction.
- Excellent anti-UV protection integral to the polyester, reduces fading of textiles, furniture, and works of art.
- Scratch resistance coating: increased longevity and easy cleaning.
- Interior installation.