



www.xegermany.de

X^e PPF Technical Data

- Hardness Durometer ASTM D-224 **Shore 60 D**
- Tensile strength ASTM D-882 **60 MPa**
- Elongation at break ASTM D-882 **500%**
- Gloss, 60° OTM 3-309 **>80**
- Tear Strength (kg) ASTM D-1938 **10.5kg**
- UV resistance A10' **No change**
- Shrinkage..... 30 min at 120°C **<1%**
- Thickness without liner **200 μ**

Features & Benefits

- Virtually invisible shield that helps protect vehicle's appearance.
- Helps defend against abrasions, nicks and scratches from insects, small road debris, and winter sand and salt (year-round protection).
- Applicable to bonnets, hoods, mirror, bumpers, fenders, radiator covers, door handles, door edges, and more.
- Helps to maintain investment and to maximise future trade-in value.
- Professional installation by qualified dealers ensure quality.
- 5-year manufacturer's warranty